

## Sunrise Petroleum FZC

P.O. Box 42553, HFZA, Sharjah, U.A.E

Ph: +971 6 5262 871 & Fax: +971 6 5262 873

Website: [www.sunrisepetroleum.com](http://www.sunrisepetroleum.com)

# Products Specification

## Bitumen

### Cut Back Bitumen Specifications

Characteristics	ASTM Method	Results	MC30	MC70	MC250
Kinematic viscosity at 60°C	D-2170	CST	30/60	70/140	250/500
Flash Point	D-1310	°C	38	38	66
Residue from distillation to 360°C, Min	D-402	% vol	50	55	67
<b>Test on Residue from Distillation</b>					
Penetration at 25°C, 100g, 5 Sec	D-5	CM	120/250	120/250	120/250
Ductility at 25°C, Min	D-113	CM	100.0	100.0	100.0
Solubility in Trichloroethylene, Min	D-2042	%	99.0	99.0	99.0
Water, Max	D-95	% Vol	0.2	0.2	0.2

Sunrise Petroleum FZC

P.O. Box 42553, HFZA, Sharjah, U.A.E

Ph: +971 6 5262 871 & Fax: +971 6 5262 873

Website: [www.sunrisepetroleum.com](http://www.sunrisepetroleum.com)